

Cable Description	40% COPPERWELD®COPPER CLAD STEEL 4 AWG LOW CARBON ANNEALED CAMO Bare, Copper Clad Steel, Copper metallurgically bonded to steel, Dead soft annealed, Low Carbon, 40% Conductivity, Chemically processed to alter surface color from copper to a shade of grey.		
Cable Specifications	ASTM B910 – Standard Specification for Annealed Copper-Clad Steel Wire		
Catalog Number	Q6C2043A-CAMO		
			
PHYSICAL DATA	Diameter of Individual Wires	5.19 (0.204)	mm (inch)
	Temper	Annealed	
	Cross Section of Area	21.15 (41.7)	mm ² (kcmil)
	Linear weight	174 (117)	kg/km (lbs/1000 ft)
	Min. Tensile	276 (40)	N/mm ² (ksi)
	Min. Elongation	15	%
ELECTRICAL DATA	Max. Conductor DC Resistance at 20°C	2.14 (0.65)	Ω/km (Ω/1000 ft)
	Conductivity	40	%
All materials contained in this document are the intellectual property of Copperweld Bimetallics, LLC., and protected by copyright laws. None of its content may not be reproduced, republished, distributed, transmitted, displayed, broadcast or otherwise exploited in any manner without the express prior written permission of Copperweld Bimetallics, LLC. For more information, contact engineering@copperweld.com .			